

August, 2016

3M™ Adhesive Transfer Tape 6035PC

Product Description

Finite Element Analysis (FEA) data is available for this product at: 3m.com/FEA

3M™ Acrylic Adhesive Transfer Tape 6035PC is a 5 mil transfer tape formulated for low fog characteristics. The 300MP adhesive is suitable for bonding to most substrates including foams, fabrics and substrates with rough or textured surfaces.



General Information

- 3M 6035PC meets automotive OEM fogging specifications
- Provides excellent bond to a wide variety of surfaces.
- High initial tack for quick and easy assembly line application.
- High temperature resistance to withstand environmental conditions normally associated with automotive interiors.

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Property	Values		Method
Total Tape Thickness	0.127 mm	5 mil	ASTM D3652
Adhesive Type	#300MP Acrylic Adhesive		
Liner	58# Polycoated Kraft Paper		
Liner Print	None		
Liner Thickness	0.107 mm	4.2 mil	

Typical Performance Characteristics

90° Peel Adhesion		Dwell/Cure Time	Dwell Time Units	Temp C	Temp F	Environmental Condition	Substrate	Backing	Notes
11.2 N/cm		15	min	23C	72F	50%RH	Stainless Steel	2 mil Aluminum Foil	
102 oz/in	14.3 N/cm	15	min	23C	72F	50%RH	Stainless Steel	2 mil Aluminum Foil	12 in/min (300 mm/min)
9.7 N/cm		15	min	23C	72F	50%RH	Polycarbonate (PC)	2 mil Aluminum Foil	12 in/min (300 mm/min)
89 oz/in		15	min	23C	72F		Polycarbonate (PC)	2 mil Aluminum Foil	
131 oz/in		72	hr	23C	72F	50%RH	Stainless Steel	2 mil Aluminum Foil	12 in/min (300 mm/min)
18.2 N/cm	166 oz/in	72	hr	70C	158F	50%RH	Stainless Steel	2 mil Aluminum Foil	12 in/min (300 mm/min)
10 N/cm	93 oz/in	72	hr	23C	72F	50%RH	ABS	2 mil Aluminum Foil	12 in/min (300 mm/min)
8 N/cm	73 oz/in	72	hr	23C	72F	50%RH	Polypropylene (PP)	2 mil Aluminum Foil	12 in/min (300 mm/min)

Table continued on next page

Typical Performance Characteristics (continued)

90° Peel Adhesion		Dwell/Cure Time	Dwell Time Units	Temp C	Temp F	Environmental Condition	Substrate	Backing	Notes
10.5 N/cm	96 oz/in	72	hr	23C	72F	50%RH	Polycarbonate (PC)	2 mil Aluminum Foil	12 in/min (300 mm/min)
7.3 N/cm	67 oz/in	72	hr	70C	158F	50%RH	Polycarbonate (PC)	2 mil Aluminum Foil	12 in/min (300 mm/min)
6.9 N/cm	63 oz/in	72	hr	70C	158F	50%RH	Polypropylene (PP)	2 mil Aluminum Foil	12 in/min (300 mm/min)
8.5 N/cm	78 oz/in	72	hr	70C	158F	50%RH	ABS	2 mil Aluminum Foil	12 in/min (300 mm/min)

Property: 90° Peel Adhesion
Method: ASTM D3330

Environmental Resistance		Dwell/Cure Time	Dwell Time Units	Temp C	Temp F	Environmental Condition
7.1 N/cm	65 oz/in	1	hr	23C	72F	Gasoline
4.3 N/cm	39 oz/in	1	hr	23C	72F	MEK
9.7 N/cm	89 oz/in	4	hr	23C	72F	Weak Acid (pH 4)
8.9 N/cm	81 oz/in	4	hr	23C	72F	Weak Base (pH 10)
12.4 N/cm	114 oz/in	72	hr	49C	120F	Oil 10W30
14.7 N/cm	134 oz/in	100	hr	23C	72F	Water
15.3 N/cm	140 oz/in	7	day	32C	90F	90%RH
14.7 N/cm	134 oz/in	72	hr			Temperature Cycling: 4 Hours at 158°F (70°C). 4 Hours at -20°F (-29°C). 16 Hours at Room Temperature. Repeat three times
12.4 N/cm	113 oz/in	72	hr	23C	72F	Salt water (5 wt% in water)
20.9 N/cm	191 oz/in	30	day			UV exposure

Property: Environmental Resistance
Test Name: 90° Peel Adhesion
Substrate: Stainless Steel
Backing: 2 mil Aluminum Foil
notes: 12 in/min (300 mm/min)

Typical Performance Characteristics (continued)

Property	Values		Test Condition
Short Term Temperature Resistance	121 °C	250 °F	Short Term (minutes, hour)
Long Term Temperature Resistance	93 °C	200 °F	Long Term (day, weeks)
UV Resistance	Adhesive is resistant to oxidation and ozone when exposed to air or ultraviolet light.		
Flammability Test	Pass FMVSS 302/SAE J369		
Automotive Fogging Test	99		SAE J1756 @ 100°C

Typical Environmental Performance

Property	Values
Humidity Resistance	No adverse effect on the bond after exposure to 100% relative humidity at 100°F (38°C)
Bond Build-Up	The bond strength of the adhesive increases as a function of time and temperature.

Storage and Shelf Life

Product retains its performance properties for 24 months from date of manufacture if properly stored at room temperature conditions of 72°F (22°C) and 50% relative humidity.

Trademarks

3M is a trademark of 3M Company.

References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/company-us/all-3m-products/~/3M-Adhesive-Transfer-Tape-6035PC/?N=5002385+3293240982&rt=rud
Safety Data Sheet SDS	https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=6035PC

3M™ Adhesive Transfer Tape 6035PC

Family Group

	6035PC	6035PL	6038PC	6038PL
Short Term Temperature Resistance (°C) Test Condition: Short Term (minutes, hour)	121	121	121	121
Long Term Temperature Resistance (°C) Test Condition: Long Term (day, weeks)	93	93	93	93
Total Tape Thickness (mm)	0.127	0.127	0.203	0.203
Adhesive Type	#300MP Acrylic Adhesive	#300MP Acrylic Adhesive	#300MP Acrylic Adhesive	#300MP Acrylic Adhesive
Liner	58# Polycoated Kraft Paper	83# Polycoated Kraft Paper	58# Polycoated Kraft Paper	83# Polycoated Kraft Paper
Liner Thickness (mm)	0.107	0.157	0.107	0.157

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.

